



Ballet Universal

Parameters	Standard Used	Units	Measured
Substance	ISO 536	g/m ²	80 +/- 2
Thickness	ISO 534	µm	106 +/-3
Bulk	ISO 534		1,33
Moisture	ISO 287	%	
Smoothness	ISO 8791	Bendtsen ml/min	220 +/- 50
Formation	Kajaani	Kajaani Index	
Whiteness	ISO 11475 ISO Brightness 2470-2	CIE %	146 +/- 3 105 +/- 2
Opacity	ISO 2471	%	93 +2/-1
Stiffness	ISO 2493	m/N	115 +/- 15 (MD) 55 +/- 10 (CD)
Porosity			

References:

- * ISO 14001 - Environmental
 - * ISO 18001 - OSHAS - Health & Safety
 - * ISO 9001:2000 - Quality Systems
-