



Ballet Brillant

| Parameters | Standard Used | Units | Measured |
|------------|-------------------------|-------------------|-----------------------------------|
| Substance | ISO 536 | g/m ² | 80 +/- 3 |
| Thickness | ISO 534 | µm | 113 +/- 3 |
| Bulk | ISO 534 | | 1,41 |
| Moisture | ISO 287 | % | 3,8 - 5,0 |
| Smoothness | ISO 8791 | Bendtsen ml/min | 180 +/- 50 |
| Formation | Kajaani | Kajaani Index | |
| Whiteness | ISO 11475 ISO 2470-2 | CIE Brightness | 170 +/- 2 112 +/- 2 |
| Opacity | ISO 2471 | % | 94 +2/-1 |
| Stiffness | ISO 2493 | m/N | 140 +/- 15 (MD) 65 +/- 15 (CD) |
| Porosity | | | |

References:

- * ISO 14001 - Environmental
 - * ISO 18001 - OHSAS - Health & Safety
 - * ISO 9001:2000 - Quality Systems
 - * ISO 9706 - Ageing Resistance
-