



Ballet Premier

Parameters	Standard Used	Units	Measured
Substance	ISO 536	g/m ²	80 +/- 3
Thickness	ISO 534	µm	108 +/- 3
Bulk	ISO 534		1,35
Moisture	ISO 287	%	4,0 +/- 0,5
Smoothness	ISO 8791	Bendtsen ml/min	180 +/- 50
Formation	Kajaani	Kajaani Index	
Whiteness	ISO 11475 Brightness ISO 2470-2	CIE %	161 +/- 2 109,5 +/- 2
Opacity	ISO 2471	%	93 +2/- 1
Stiffness	ISO 2493	m/N	115 +/- 10 MD 55 +/- 5 CD
Porosity			

References:

- * ISO 14001 - Environmental
 - * ISO 18001 - OHSAS - Health & Safety
 - * ISO 9001:2000 - Quality Systems
 - * ISO 9706 - Ageing Resistance
-