



## Technical Data Sheet

### Rey Office

Parameters	Standard	Unit	Measurement
Substance	ISO 536	g/m <sup>2</sup>	80 +/- 2
Thickness	ISO 534	µm	109 +/- 3
Bulk	ISO 534		1,36
Moisture Content	ISO 287	%	4,4 +/- 0,6
Roughness	ISO 8791	Bendtsen ml/min	230 +/- 50
Whiteness	ISO 11475	CIE	161 +/- 3
Brightness D65	ISO 2470-2	%	109,5 +/- 1
Opacity	ISO 2471	%	92 +/- 2
Stiffness MD	ISO 2493	mN	130 +/- 15
Stiffness CD	ISO 2493	mN	50 +/- 15

#### Production sites:

The production mills operate in compliance with the following standards



#### Special Attributes:



References:  
Product is made taking into account requirements of DIN EN 12281  
Product made from ECF Pulp  
ISO 45001 - Health & Safety

The data presented can be changed without notice.

International Paper EMEA  
Chaussée de la Hulpe 166  
1170 Brussels, Belgium  
Tel.: +32 2 774 1211  
Fax: +32 2 774 1299  
Extract date: 19.08.2021